

TECHNICAL INFORMATION & SPECIFICATIONS



PRODUCT INFORMATION

CONSTRUCTION	Polypropylene Based (PVC Free)	Ceramic Mineral Board (Homogenous)
THICKNESS	5.5 mm nominal (4.5+1 mm)	
WOOD - PLANK DIMENSIONS	1290 mm x 203 mm	50.78" x 7.99"
WOOD - PLANKS PER CARTON / SF	9 planks	25.37 SF
STONE - TILE DIMENSIONS	638 mm x 310 mm	25.12" x 12.20"
STONE - TILES PER CARTON / SF	12 tiles	25.55 SF
JOINT (Installation System)	Glueless click	Megaloc - angle drop
EDGE DETAIL	Micro-Bevel Edge	
FINISH / WEAR LAYER	Sealtec Plus	0.20 mm
DENSITY	1 Plank = 1.91 kg	1,480 kg/m ³ / 92.4 lbs/ft ³
LIMITED WARRANTY	Lifetime Limited Residential	10 Years Light Commercial
COUNTRY OF MANUFACTURE	Germany	

STANDARDS - MANUFACTURING & USAGE - PAGE 1

	Performance	Test Method	Measure
EN 16511	Geometric properties	ISO 24337	Rqmts. According to Table 1 fulfilled
	Abrasion resistance	EN 15468 (Falling-Sand Method)	Exceeds rqmts, > 7000 Revolutions
	Resistance against impact	EN 13329	Meets rqmts, Big ball > 1800 mm
	Microscratch resistance	EN 16094	Meets rqmts, MSR-A2
	Effect of a castor chair	EN 425	Meets rqmts, no visible change/damages
	Effect of a furniture leg	EN ISO 16581	Meets rqmts, no visible change/damages
	Determination of static indentation	EN ISO 24343	Exceeds rqmts, 0.1 mm
	Resistance against staining	EN 438-2	Exceeds rqmts, Grade 5 for Groups 1, 2 & 3
	Locking strength	ISO 24334	Exceeds rqmts, Long side > 2.5 kN/m Short side > 4.5 kN/m
	Dimensional stability	EN ISO 23999	Exceeds rqmts, Length 0.1% / Width 0.1%
ASTM F3261	Size, tol. ≥24 in. ≤48 in.	ISO 24337 - Tile, Plank	Meets and/or Exceeds
	Size, tol. ≥48 in.	ISO 24337 - Plank	Meets and/or Exceeds
	Thickness	ASTM F387	Meets and/or Exceeds
	Squareness	ISO 24337	Meets and/or Exceeds
	Flatness, max, inches (width & length)	ISO 24337	Meets and/or Exceeds
	Openings, avg / max, mm	ISO 24337	Meets and/or Exceeds
	Ledging, avg / max, mm	ISO 24337	Meets and/or Exceeds
	Residual indentation, in.	ASTM F1914	Exceeds rqmts, 0.002 inch @ 75 lbs
	Surface integrity	ASTM F1914	Meets and/or Exceeds @ 140 lbs
	Dimensional stability	ASTM F2199	Exceeds rqmts, Length 0.1% / Width 0.1%
	Curl, inches	ASTM F2199	Exceeds rqmts, 1 mm
	Resistance to chemicals	ASTM F925	Exceeds rqmts, "0 - No Change"
	Resistance to heat	ASTM F1514	Exceeds rqmts, Delta E Rating (ΔE) < 0.5
	Resistance to light	ASTM F1515	Exceeds rqmts, Delta E (ΔE) Rating < 1
	Static Load	ASTM F970	Exceeds rqmts, 1,200 psi 0.005" (0.13mm)

SUSTAINABILITY - GREENGUARD Gold Certified. This Standard includes health-based criteria to ensure that products are acceptable for use in environments such as schools and health care facilities. In addition to limiting emissions of more than 360 VOCs and total chemical emissions, comply with requirements of the state of California Department of Public Health (CDPH) Standard Method for the Testing and Evaluation of VOC Emissions from Indoor Sources Using Environmental Chambers, Version 1.1 (2010) (also known as California Section 01350 or CDPH v.1.1-2010)



Notice: This edition replaces all previous versions.

Effective: 10 Aug 2020

888-255-3412 - WWW.INHAUSSURFACES.COM

TECHNICAL INFORMATION & SPECIFICATIONS



PRODUCT INFORMATION

CONSTRUCTION	Polypropylene Based (PVC Free)	Ceramic Mineral Board (Homogenous)
THICKNESS	5.5 mm nominal (4.5+1 mm)	
WOOD - PLANK DIMENSIONS	1290 mm x 203 mm	50.78" x 7.99"
WOOD - PLANKS PER CARTON / SF	9 planks	25.37 SF
STONE - TILE DIMENSIONS	638 mm x 310 mm	25.12" x 12.20"
STONE - TILES PER CARTON / SF	12 tiles	25.55 SF
JOINT (Installation System)	Glueless click	Megaloc - angle drop
EDGE DETAIL	Micro-Bevel Edge	
FINISH / WEAR LAYER	Sealtec Plus	0.20 mm
DENSITY	1 Plank = 1.91 kg	1,480 kg/m ³ / 92.4 lbs/ft ³
LIMITED WARRANTY	Lifetime Limited Residential	10 Years Light Commercial
COUNTRY OF MANUFACTURE	Germany	

STANDARDS - MANUFACTURING & USAGE - PAGE 2

	Performance	Test Method	Measure
SUPPLEMENTARY	R-value / Thermal Resistance	EN 12667	0.033 (m ² K) / W
	Light fastness	EN 13329	Meets and/or Exceeds
	Thickness Swelling	NALFA 3.2	Exceeds rqmts, < 0.9%
	Surface Bond	NALFA 3.10	Exceeds rqmts, 2.10 N/mm ²
	Deflection	ASTM F1304	Meets and/or Exceeds
	Static Propensity (Step & Scuff)	AATCC 134	Maximum Average 2.5 kv Negative
	Slip resistance	ASTM D2047	> 0.5 SCOF Dry
		ANSI / NFSI B101.3	≥ 0.3 DCOF Wet
	Resistance to Fungi	ASTM G21	Rating 1 (wk1-0, wk2-0, wk3-0, wk4-1)
	Heavy Metals - Sb, As, Ba, Cd, Cr, Hg, Pb, Se	EN 15102 to DIN EN 71-3 and DIN EN 12149	Passes, Very Low or Not Detectable
	Flammability	ASTM D2859	Passes, (face side)
	Smoke density	ASTM E662	Passes, 83 Flaming / 447 Non-flaming
	Critical radiant flux	ASTM E648	Passes, > 0.45 W/cm ² / Class I
SOUND	Airborne Sound Transmission Loss	ASTM E90 & ASTM E413 w/drop ceiling without drop ceiling	Sound transmission loss STC 53 dB * Sound transmission loss STC 50 dB *
	Impact Sound Transmission	ASTM E492 & ASTM E989 w/drop ceiling without drop ceiling	Impact insulation class IIC 61 dB * Impact insulation class IIC 55 dB *
	Effectiveness of Floor Coverings in Reducing Impact Sound Transmission	ASTM E2179	Increase impact insulation ΔIIC 22 dB *

SUSTAINABILITY - GREENGUARD Gold Certified. This Standard includes health-based criteria to ensure that products are acceptable for use in environments such as schools and health care facilities. In addition to limiting emissions of more than 360 VOCs and total chemical emissions, comply with requirements of the state of California Department of Public Health (CDPH) Standard Method for the Testing and Evaluation of VOC Emissions from Indoor Sources Using Environmental Chambers, Version 1.1 (2010) (also known as California Section 01350 or CDPH v.1.1-2010)

* Tested with attached underlayment 1.0 mm Extruded Polyolefin

Notice: This edition replaces all previous versions.

Effective: 10 Aug 2020